

Contents

1	Introduction	1
2	Fundamentals	5
2.1	Properties of III-nitrides	5
2.2	Epitaxial growth techniques	8
2.2.1	Molecular beam epitaxy	8
2.3	Characterization methods	12
2.3.1	High resolution X-ray diffraction	12
2.3.2	Atomic force microscopy	15
2.3.3	Luminescence spectroscopy	17
3	MBE of cubic GaN and cubic AlGaN	21
3.1	<i>In situ</i> growth regime characterization of cubic GaN	21
3.1.1	Adsorption and desorption of Ga on c-GaN	21
3.1.2	Kinetic model	26
3.1.3	Growth experiments	29
3.2	Growth and characterization of cubic AlGaN/GaN heterostructures . . .	35
4	Growth of cubic AlGaN/GaN quantum wells	43
4.1	Growth and structural properties of cubic AlGaN/GaN quantum wells .	43
4.2	Photoluminescence of cubic AlGaN/GaN quantum wells	46
5	AlN/GaN superlattices for intersubband spectroscopy	53
5.1	Intersubband transitions	53

5.2	Growth of c-AlN/GaN superlattices	60
5.3	Structural properties of AlN/GaN SLs	64
5.4	Optical properties of AlN/GaN SLs	66
6	Conclusion	71
7	Appendix	73

List of Figures

2.1	Unit cell of a) the zincblende structure and b) the hexagonal structure. . .	6
2.2	Different polarities in hexagonal GaN	7
2.3	Band profiles and carrier distributions in cubic and hexagonal AlGaIn/GaN quantum wells; a) the cubic AlGaIn/GaN DH structure and b) the hexagonal AlGaIn/GaN DH structure	8
2.4	Schematic cross section of an MBE setup.	9
2.5	Schematic diagram of the RHEED diffraction geometry, showing reflection and transmission diffraction, as well as the straight-through (0,0) beam. .	10
2.6	Typical RHEED-pattern of c-GaN during growth interruption. A (2×2) reconstruction of the (-110) azimuth is observed.	11
2.7	Sketch of the diffraction geometry. The exact Bragg condition for (hkl) planes is fulfilled, if the scattering vector \vec{Q} ends at a reciprocal lattice point (hkl).	13
2.8	Schematic drawing of the Phillips X'Pert MRD consisting of X-Ray tube, hybrid monochromator, Euler cradle and detector.	15
2.9	Schematic drawing of an AFM setup.	16
2.10	Schematic diagram of radiative transitions in a semiconductor; (e, h) represents intrinsic band to band, (X) free exciton, (D^0, X) , (A^0, X) represents bound excitons to donator or acceptor and (D^0, h) , (h, A^0) free to bound, (D^0, A^0) donor to acceptor transitions.	18
2.11	Schematic diagram of the photoluminescence setup.	19

3.1	a) A sketch of the sample structure with the RHEED geometry. b) A (2×2) reconstruction of a c-GaN surface during growth interruption. The red rectangle indicates the area where the RHEED intensity was recorded.	22
3.2	The intensity of a reflected high energy electron beam (RHEED intensity) versus time measured during the evaporation of Ga onto c-GaN at a substrate temperature of $T_S = 720^\circ C$. The Ga-fluxes are indicated. The spectra are normalized to one and vertically shifted for clarity.	23
3.3	RHEED intensity transient for a Ga-flux of $F_{Ga} = 4.3 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$ and $7.5 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$.	24
3.4	RHEED intensity transients for Ga-fluxes of $4.3 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$ and $7.5 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$. After a transition time Δt_k a kink in the transients is observed. The estimated Ga-coverage is plotted on the right side.	25
3.5	RHEED intensity transients for a Ga-flux of $2 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$. The red curves show the simulations for a flux of $2 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$ and three different desorption fluxes as indicated in the figure. Good agreement was achieved for a desorption flux of $1.6 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$.	27
3.6	RHEED intensity transients for two Ga-fluxes together with simulations as indicated in the figure. Good agreement was achieved within the linear decrease of the RHEED intensity.	28
3.7	RHEED intensity transients measured during the growth of c-GaN, which started after opening the N source. The RHEED intensity measured during growth shows the amount of excess Ga (indicated in the figure) on the c-GaN surface. Ga-fluxes are 4.4×10^{14} , 3.2×10^{14} and $1.2 \times 10^{14} \text{ cm}^{-2} \text{ s}^{-1}$ for the coverages of 1, 0.8, and 0 ML, respectively.	29
3.8	Root-mean-square (RMS) roughness of c-GaN layers measured by $5 \times 5 \mu\text{m}^2$ scans vs. Ga-flux during growth. The corresponding values of the Ga-coverage during growth are also included. Minimum roughness is obtained with an excess coverage of 1 ML. The line is added for better overview.	30

3.9	$\omega - 2\Theta$ scan of the (002) reflex of sample 1287. The inset shows the ω -scan of this sample revealing a FWHM of 16 arcmin.	31
3.10	Full width at half maximum (FWHM) of c-GaN layers vs. Ga-flux during growth. The corresponding values of the Ga-coverage during growth are also included. Minimum linewidth is obtained with an excess coverage of 1 ML. The line is a guide for the eyes.	32
3.11	Line width of rocking curve (FWHM) of the (002) reflex of cubic GaN epilayers grown on 3C-SiC(001) substrates versus thickness of the GaN epilayers.	34
3.12	Schematic sketch of an AlGa _x N/GaN heterostructure	35
3.13	RHEED intensity measured during initial growth of $c - Al_{0.25}Ga_{0.75}N$. The RHEED intensity after opening the N shutter yields the amount of excess Ga on the c-GaN surface. After opening the Al shutter RHEED intensity oscillations are observed indicating a two-dimensional growth mode with a rate of 177 nm/h.	37
3.14	Reciprocal space map of the c-GaN (-1-13) reflex of sample 1117. The c-AlGa _x N layer is pseudomorph to the c-GaN buffer layer. The Al-mole fraction is $x=0.3$	38
3.15	Reciprocal space map of the c-GaN (-1-13) reflex of sample 1360. The c-AlGa _x N layer is relaxed to the c-GaN buffer layer. The Al-mole fraction is $x=0.7$	39
3.16	XRD rocking curve of the (002) reflex of sample 1117. The full width at half maximum of the c-GaN and the c-AlGa _x N layer are nearly identical.	40
3.17	Relation between the Al mole fraction x of c- Al _{x} Ga _{$1-x$} N and the ratio of Al-flux to the total metal flux for films grown under 1ML Ga-coverage. The mole fraction x was determined by HRXRD.	41
3.18	RMS surface roughness of different c-Al _{x} Ga _{$1-x$} N/GaN heterostructures with an Al mole fraction between $x=0$ and $x=1$. Layers were grown with a 1 ML Ga coverage. The line is a guide for the eyes.	42

4.1	Schematic Sketch of a multiple quantum well structure	44
4.2	Measured $\omega - 2\Theta$ scan of a 15-fold $\text{Al}_{0.3}\text{Ga}_{0.7}\text{N}/\text{GaN}$ structure (solid line) and simulated data (dotted line). The well and the barrier width are 3 nm and 6 nm.	45
4.3	Reciprocal space map around the asymmetric (-1-13) reflex of sample 1372. The quantum wells are pseudomorph to the c-GaN buffer.	46
4.4	Room temperature photoluminescence of cubic $\text{Al}_{0.15}\text{Ga}_{0.85}\text{N}/\text{GaN}$ single and multiple quantum well structures. The QW transition energy is $E=3.30$ eV and the linewidth is 90 meV for the SQW and 103 meV for the MQW.	47
4.5	Low temperature photoluminescence of cubic $\text{Al}_{0.15}\text{Ga}_{0.85}\text{N}/\text{GaN}$ SQW and MQW structures. The QW transition energy is $E=3.33$ eV and 3.35 eV and the linewidth is 64 meV and 80 meV, respectively	48
4.6	Schematic view of a quantum well without and with built-in field. Electrons and holes are localized in opposite corners leading to a red-shift of the lowest transition and to a reduction of the oscillator strength compared to the flat band case in the cubic system [53].	49
4.7	Energy difference of cubic and hexagonal AlGaIn/GaN QWs as a function of well width [54]. The full curve for the cubic QWs was calculated using the self-consistent Poisson-Schrödinger model [55]. The hexagonal QWs show a red-shift of the transition energy below the band gap of hexagonal GaN.	50
5.1	Schematic sketch of an intersubband transition in the conduction band after absorption of a photon with equal energy to the difference between the ground state E_0 and the first excited state E_1 [70].	54
5.2	The (a) bound-to-bound, (b) bound-to-quasi-bound and (c) bound-to-continuum transitions of electrons in the conduction band are depicted.	55
5.3	Band gap of $\text{Al}_x\text{Ga}_{1-x}\text{N}$ and the conduction band offset of $\text{GaN}/\text{Al}_x\text{Ga}_{1-x}\text{N}$ as a function of the Al mole fraction.	56

5.4	Schematic sketch of transitions in quantum wells with different well thicknesses. The blue curve indicates case (a) the red curve case (b) and the green curve case (c) [70].	57
5.5	Typical quantum well design structure with two bound states. Quantum wells are shown without bias voltage on the left side and with applied bias voltage on the right side.	58
5.6	Mesa structure of a typical quantum well infrared photo detector. A bias voltage is supplied and a photocurrent is measured.	59
5.7	Transition energies of AlN/GaN multiple quantum well versus the QW thickness calculated by a self-consistent Poisson-Schrödinger model. . . .	60
5.8	Schematic sketch of an AlN/GaN MQW structure for intersubband transitions. The thicknesses of the wells vary between 1.3 and 1.9 nm, the thickness of the barriers is 1.5 nm.	61
5.9	RHEED timescan of sample 1518 on an extended scale. The shutter sequence and the coverage of 1 ML during c-GaN growth is indicated in the figure.	62
5.10	RHEED intensity versus time during the growth of an AlN/GaN superlattice of sample 1518. The Fig. shows the RHEED intensities of period 2 and 3 and of period 18 and 19. The shaded area indicates the growth of the individual layer. The scans are vertically shifted for clarity.	63
5.11	ω - 2Θ scan and simulated data of the (002) reflex of sample 1518. The sample consists of a 20-fold AlN/GaN MQW structure. The simulation reveals a barrier thickness of 1.35 nm and a QW thickness of 1.75 nm. . . .	64
5.12	An SEM image of a waveguide with approximately 2 mm width and 5 mm length [70].	66
5.13	Illustration of light propagating through a waveguide.	66
5.14	Room-temperature absorbance spectra of 4 AlN/GaN MQW structures and of a substrate. Absorption was observed in the range of 0.6 eV to 0.8 eV (1.6 μm to 2 μm). The spectra are vertically shifted for clarity.	67

5.15 Intersubband absorption of four AlN/GaN MQWs. The spectra are plotted after subtraction of the substrate background in the spectral range between 0.5 eV and 1.1 eV ($1.1 \mu m$ and $2.5 \mu m$). A shaded area indicates the wavelength of $1.55 \mu m$. The FWHM of all samples is about 200 meV. 68

5.16 Simulation of the conduction band of sample 1518. Two bounded states are observed within the quantum well. The shaded area indicates the distribution of the first excited state E_1 69

5.17 Transition energies of AlN/GaN multiple quantum wells versus the QW thickness as shown in Fig. 5.7. The experimental data show good agreement with the calculated data. 70