

Contents

Preface	1
Notation	5
1 Introduction to dislocation theory	9
1.1 Concept of dislocation	9
1.2 Partial dislocations	18
1.3 Plasticity in a crystal under external stress	21
1.3.1 Transition from elastic deformation to Stage I	22
1.3.2 Stage I (easy glide)	22
1.3.3 Stage II (rapid hardening)	25
1.3.4 Stage III	27
2 A gauge principle for the dislocation theory	29
2.1 Definition of dislocation density and current	30
2.2 Equations of dislocation dynamics <i>à la</i> Maxwell	34
2.3 The central idea: the superconductor as model for the crystal deformed plastically [68]	52
2.4 Formulating the model in four steps	57
2.4.1 Step 1: the gauge invariant energy for dislocation configurations	57
<i>Note.</i> Gauge invariance and the Noether theorem.	64
2.4.2 Step 2: putting the model on a discrete lattice and introducing some multivalueness in the gauge field A_μ^α	69
2.4.3 Step 3: scale η and partition function \mathcal{Z} for equilibrium phase transitions	81
<i>Note.</i> The analogue to the Abrikosov model's $\hbar c$	86
2.4.4 Step 4: incorporating the effect of the temperature	89
2.5 Gauge invariant correlation functions	91
2.5.1 Meaning of $W(C)$	94
<i>Note.</i> Behaviour of $W(C)$ in the elastic stage.	96
<i>Note.</i> The complementary correlation function $H(\vec{r}_b - \vec{r}_a)$ in the 3- dimensional Higgs model.	104
3 Applications of the dislocation model: the different plastic behaviours in the hardening curve	107
3.1 Stage I in a crystal and Shubnikov state in a superconductor	107

3.2	Stage II and the confinement of the current of gliding dislocations	111
3.3	Phase diagram for the 3-dimensional lattice dislocation model at $T = 0$	115
	<i>Note.</i> The phase transition in the 3-dim. non-compact model at $T = 0$ described through the continuum model.	122
3.4	Phase diagram for the 3-dimensional lattice dislocation model at high temperatures	125
3.5	A speculative short excursus: modellizing disordered single crystals and the introduction of a fourth spatial dimension	131
4	Conclusions and further development	141
4.1	Conclusions	141
4.2	Ansatz for the connection to the Anthony's model of Irreversible Thermodynamics	146
	Acknowledgments	163
A	The Abrikosov model for Superconductivity	173
A.1	The Meissner phase	173
A.2	The Shubnikov phase	176
	A.2.1 Energy of one flux line in the mixed or Shubnikov state	176
	<i>Note.</i> The non-relativistic Higgs mechanism.	178
	<i>Note.</i> The superconducting film.	182
	A.2.2 Range $H_{\text{ext}} - H_{c1} \ll H_{c1}$	186
	A.2.3 Range $H_{c1} \ll H_{\text{ext}} \ll H_{c2}$	186
	A.2.4 Range $H_{\text{ext}} \approx H_{c2}$	187
B	Informal introduction to homotopy theory. Line and point defects.	191
B.1	The first homotopy group π_1	191
B.2	Applications of group π_1 : line defects in a 3-dimensional system (I)	197
	<i>Note.</i> About the spontaneous symmetry breakdown (I).	201
	<i>Note.</i> About the spontaneous symmetry breakdown (II).	210
B.3	A little excursus: Lie groups and Lie algebras	213
B.4	Applications of group π_1 : line defects in a 3-dimensional system (II)	219
	<i>Note.</i> Isospace rotations of isovector Ψ^a	230
B.5	Scalar field coupled to an $SO(3)$ gauge field: the " $SO(3)$ "-superconductor	233
	<i>Note.</i> Magnetic monopoles.	235
B.6	The 't Hooft–Polyakov monopole	243
	B.6.1 Maxwell equations for $F_{\mu\nu}$	246
	<i>Note.</i> Calculation of $\epsilon_{\lambda\mu\nu}\epsilon_{abc} (\partial_\lambda \hat{\Psi}^a) (\partial_\mu \hat{\Psi}^b) (\partial_\nu \hat{\Psi}^c)$	247
	B.6.2 The energy of the 't Hooft–Polyakov monopole	249
B.7	The most important part of the Appendix: monopole and vortex configurations with an isotensor $\Psi^{ab\dots}$ of second (and higher) rank	251
	<i>Note.</i> Flux lines (or vortices) attached to a monopole.	263
	B.7.1 The fundamental theorem on π_1 and on π_2	265

B.7.2	Entanglement of line defects in 3-dim. real space [69]	271
B.7.3	The scalar irreducible isotensor Ψ^{ab} of second rank	274
	<i>Note.</i> The scalar isotensor describing a topologically stable point defect in a 3-dim. physical space.	275
	<i>Note.</i> The general form of potential $V(\Psi)$: informal comments.	291
B.7.4	The scalar irreducible isotensor Ψ^{abc} of third rank	297
C	Correlation functions and phase diagrams at temperature $T = 0$	307
C.1	The 2-dimensional Ising model	310
C.1.1	Peierls' proof of the nonvanishing spontaneous magnetization at large $\beta = J/\eta$	313
C.1.2	The two-point correlation function $\langle \sigma_{\vec{r}_1} \sigma_{\vec{r}_2} \rangle_{\Lambda}$	316
	<i>Note.</i> Evaluation of $(\Gamma_{\vec{r}_1 \vec{r}_2})_{\Lambda}$ at large β .	320
C.2	An illustrative method to estimate correlation functions	323
C.3	The 2-dimensional XY model	329
C.3.1	The Villain transformation in the XY model	331
	<i>Note.</i> Gaussian integrals.	334
	<i>Note.</i> About the topological fields (I) and the Villain approximation.	344
C.3.2	Different behaviours of correlation $\langle e^{i(\varphi_{\vec{r}_1} - \varphi_{\vec{r}_2})} \rangle$	347
C.4	The 3-dimensional XY model	359
	<i>Note.</i> The Faddeev-Popov recipe.	366
C.4.1	Phases in the 3-dimensional XY model	375
	<i>Note.</i> Critical point in the 3-dimensional XY model.	377
C.5	The 3-dimensional lattice Higgs model	384
C.5.1	The 3-dimensional pure compact $U(1)$ gauge model	389
	<i>Note.</i> Correlation $W(C) = \left\langle e^{i p \oint_{\text{loop } C} A_{\mu, \vec{r}}} \right\rangle$ for $p \neq 1$ at strong $ae^2\eta$.	390
	<i>Note.</i> About the topological fields (II): the Polyakov model.	397
	<i>Note.</i> The pure compact $U(1)$ gauge model in two and in four dimensions.	405
	<i>Note.</i> The pure gauge model for $p \neq 1$.	409
C.5.2	The pure $Z(2)$ gauge model	411
	<i>Note.</i> Evaluation of $W(C)$ in the dual model.	422
C.5.3	The lattice Higgs model in the Villain approximation	427
	<i>Note.</i> Calculation of $\Pi_{\vec{x}, \vec{x}'}$.	436
	<i>Note.</i> Absence of a phase transition between the region of large e^2 and the region of large $ \psi ^2$ and small e^2 when $q = 1$.	451
	<i>Note.</i> The phase diagram for the 4-dimensional and the 2-dimensional Higgs model, both compact and non-compact.	472
C.6	The lattice compact Villain-Higgs model in several different gauges	489
D	Finite Temperature Effects	509
D.1	The Transfer Matrix \hat{T} and the Hamiltonian formulation in Statistical Mechanics	509
	<i>Note.</i> Connection between Statistical and Quantum Physics.	512

	<i>Note.</i> Characterizing the phases of the 2-dim. Ising model in the Hamiltonian formulation.	521
	<i>Note.</i> Phase diagram of the d -dim. Ising model in a lattice periodic along one direction.	531
D.2	The “deconfinement” transition	540
D.2.1	The Hamiltonian formulation of the pure compact $U(1)$ gauge model	540
	<i>Note.</i> $\hat{\mathcal{G}}_{\vec{x}'}\{\psi[A_{k,\vec{x}}]\}$ for a gauge field coupled to an external source: an example. The “confining” phase (I).	547
D.2.2	The “deconfinement” transition in the pure compact gauge model at high temperatures	550
	<i>Note.</i> The “confining” phase (II).	552
D.2.3	The 3-dimensional pure compact gauge model at high temperatures [92]	559
D.2.4	The pure $Z(N)$ gauge model at high temperatures	571
	<i>Note.</i> The $Z(N)$ Ising model in the Villain approximation.	572
	<i>Note.</i> The “confining” phase (III).	582
	<i>Note.</i> The phase diagram of the d -dimensional $Z(N=2)$ gauge model in a periodic lattice along one direction at small e^2 and for $d=3,4$.	594
D.3	The phase diagram of the compact $U(1)$ Higgs model at high temperatures	611
	<i>Note.</i> Equivalence between $\mathcal{V}_{\vec{x}_1,\vec{x}_2}$ and $W(C)$ in the compact Higgs model.	615
	<i>Note.</i> Equivalence between $W(C) \sim e^{-\text{Perimeter}_C}$ at $\omega = \infty$ and $W(C) \sim \text{const.}$ at small ω , and between $W(C) \sim e^{-\text{Area}_C}$ at $\omega = \infty$ and $W(C) \sim e^{- \vec{x}_2 - \vec{x}_1 }$ at small ω	630
D.4	The phase diagram of the non-compact $U(1)$ Higgs model at high temperatures (I)	636
D.5	The phase diagram of the non-compact $U(1)$ Higgs model at high temperatures (II)	649
D.5.1	Connection to the Abrikosov model of Appendix A	649
	<i>Note.</i> Calculation of $\left\langle e^{i\varphi_{\vec{r}_1}} \exp\left[i \sum_{\vec{r},\mu} \mathcal{L}_{\mu,\vec{r}} A_{\mu,\vec{r}}\right] e^{-i\varphi_{\vec{r}_2}} \right\rangle$ for the 3-dim. non-compact Higgs model.	656
D.5.2	The effective potential $V_{\text{eff}}(\bar{\rho})$	663
	<i>Note.</i> Calculation of the effective potential: an example.	674
D.5.3	The effective potential for the pure scalar model	681
	<i>Note.</i> Calculation of $I_n(M) = \frac{1}{(n-1)!} \int_0^\infty \frac{x^{n-1}}{\sqrt{x^2 + M^2}} \frac{dx}{e^{\sqrt{x^2 + M^2}} - 1}$	695
D.5.4	The effective potential for the Abrikosov model	700
	<i>Note.</i> Generating functionals of correlation functions.	730

List of Figures

1.1	The close packed f.c.c. lattice. With the directions along the x, y, z axes defined as $[100], [010], [001]$ respectively, the plane formed for instance by the \bullet 's, is plane (111) . Note that in a cubic lattice, direction $[hkl]$ cuts normally plane (hkl) ; a denotes the lattice spacing.	10
1.2	The $[001]$ stereographic projection for f.c.c. crystals. This is the projection on the $x - y$ plane (the "picture" taken from a plane of constant positive z , with $\hat{z} = [001]$) of the intersection points of the different crystal's directions with a sphere. Symbols \circ , \triangle and \diamond denote a two-, three- and four-fold symmetry axis.	10
1.3	Applied tensile stress σ_T and projected component $\tau_{resol.}$ on the slip plane along the slip direction. If the tensile axis is held fixed, the slip changes the projection of the tensile stress on the first activated slip system. According to the usual index convention, σ_j^α denotes tension along α direction applied to the plane normal to the j direction; both α and j runs from 1 to 3.	11
1.4	Edge and screw dislocation.	12
1.5	An 8-steps path defines, according to the right-hand rule, the direction assigned to the dislocation line. Burgers vector \mathbf{b} points from the begin to the end of the path C . For an edge dislocation, the Burgers vector is orthogonal to the dislocation line and for a screw dislocation, parallel to it.	12
1.6	Example of the jog formed at screw dislocation 1 after having crossed through screw dislocation 2. Although not represented in the figure, dislocation 2 has suffered an analogous jog.	17
1.7	Frank partial dislocation after removing a part of the A layer. Below the partial dislocation, the stacking sequence is disturbed: $ABCB$	18
1.8	Burgers vector of a Frank partial dislocation.	19
1.9	Thompson's tetrahedron. The plane (111) is the plane ABC , the cover of the tetrahedron. A, B, C, D denote the vertices of the tetrahedron and greek letters $\alpha, \beta, \gamma, \delta$ identify the possible $\{111\}$ glide planes corresponding to the corners named with latin letters in front of each plane.	20
1.10	Typical hardening curve for (resolved) shear stress versus shear strain in f.c.c. crystals at two different temperatures T_1 and T_2	21
1.11	Dislocations in Stage I for an f.c.c. Ni+40% Co alloy. Most of the dislocations are perpendicular to the glide direction g , i.e., they are edge dislocations. Glide=0.21. After [67].	23
1.12	Slip lines in Stage I for copper. Glide=0.094.	23

1.13	A Frank-Read source in silicon decorated with copper.	24
1.14	The Frank-Read source with a dislocation line pinned at the points A and B separated by a distance l	24
1.15	Lomer-Cottrell networks at early Stage II in copper at a temperature of 4.2 K. Micrograph of the primary glide plane. After [13].	25
1.16	Formation of a Lomer-Cottrell segment as in Fig. 1.15 along the intersection line between the primary plane and the secondary one. This Lomer-Cottrell lock cannot glide in any $\{111\}$ slip plane, since none of these planes can contain both the lock and its Burgers vector.	25
1.17	Dislocations in Stage II for a f.c.c. Ni+40%Co alloy. The glide direction is denoted by g : the majority of the primary dislocations are edge dislocations. In the upper right corner there are dislocations drawing an angle of 30° with the primary ones. They are the dislocations formed along the intersection line between the primary and the conjugate plane. Glide=0.70. After [67].	26
1.18	Dislocations in late Stage II for a f.c.c. Ni+40%Co alloy. The primary and secondary dislocations (and their products) are grouped together in cords. Between these cords there are still regions of very low dislocation density. Glide=0.83, with g the glide direction. After [67].	26
1.19	“Disc”-structure in the primary plane at the end of Stage II and at the begin of Stage III in copper, where $[101]$ denotes the glide direction. The diameter of the region confined by the dense cords of Lomer-Cottrell locks is about some micrometers. After [67].	28
1.20	Slip bands in Stage III for copper with a cross-slip at A : the step height is about $1 \mu\text{m}$. (Mader et al., <i>J. Appl. Phys.</i> 28 , 53 (1963) quoted in [51]).	28
1.21	Cross-slip of the partial dislocations A and B from the “disc” in a lower primary plane to the “disc” in a higher primary one.	28
2.1	External coordinates x^k and with-material-comoving coordinates X^α . . .	30
2.2	Definition of the Burgers vector of a dislocation.	34
2.3	Plastic stages in the stress-strain curve (a) with only one slip system activated in a lead-indium type-II superconductor at a temperature of 4.2 K and at a strain rate of 10^{-4} s^{-1} . Representation (b) (in arbitrary units and as a function of the plastic shear strain) of the change in the magnetic flux density accompanying the motion of dislocations which were pinning the flux lines. Diagram (b) represents thus the change of mobile dislocation density $\alpha_{\text{glid}}^\alpha$ during the plastic deformation. For the elastic stage (zero plastic strain) there is no change in $\alpha_{\text{glid}}^\alpha$. After [77]. . .	36
2.4	Distortion of the uniform arrangement (left figure) of primary dislocations, $\partial_x (\alpha_{\text{prim}})_x^1 > 0$, due to an applied stress. According to the convention defining the indices of the stress tensor, the applied stress in the right figure is negative since the y axis points downwards: $\tau_{\text{ext}} = -(\tau_{\text{resol}})_y^1 < 0$.	41
2.5	The dislocation current in the lower primary plane, $(\mathcal{J}_{\text{prim}})_y^1 (y_0 + \Delta y)$, is smaller than at y_0 and thus crystal plane at y_0 slips over the plane at $y_0 + \Delta y$ with a velocity $v_{\text{slip}}^1 (y_0) > 0$	43

2.6	Example of a deformation of two neighbour atomic cells along direction α , whereas at the initial undeformed state the scalar field for both cells was pointing (within its internal space) in the same reference direction.	58
2.7	Left, dislocation arrangement in the rapid hardening stage with the characteristic confinement of the current of gliding dislocations within the tube delimited by “discs” of sessile dislocations. Right, complete breaking of such configuration resulting in periodically repeated pieces due to the thermal activation of cross-slip. Length ω denotes the periodicity.	90
3.1	Fraction Θ_1/G in dependence on the applied resolved shear stress for the start of the easy glide stage.	111
3.2	In the Stage II the gliding dislocations crossing the area enclosed by loop C of correlation function $W(C)$ cannot escape from the disc-structure of sessile segments. The number of the retained mobile dislocations is of the order of $N \sim 100$. Current \mathbf{E}_i^α of gliding dislocations is confined within a tube formed by these discs of section $A \sim L_{\text{glide}}^2$, with $\mathbf{E} \sim \frac{N}{A}$ obtained from the Gauss theorem applied on the closed surface S around the end of such tube.	112
3.3	Influence of the orientation in the hardening curve for copper crystals (J. Diehl, <i>Z. Metallk.</i> 47 , 331 (1956) quoted in [23] and in [51]).	115
3.4	Expected phase diagram for the 3-dimensional compact Higgs model at zero temperature for $q^\alpha = 1$, $q^\alpha = 2$ and for large q^α . Axis $ \psi ^2 = 0$ corresponds to the (compact) pure $U(1)$ gauge model, axis $e^2 = 0$ to the XY model and axis $ \psi ^2 = \infty$ is the pure $Z(q)$ gauge model. Point A is the critical value (or second-order transition point) of the 3-dimensional XY model: $(a \psi ^2/\eta)_{\text{crit}} = 0.322$; point B denotes the critical value of the 3-dimensional $Z(2)$ gauge model: $(ae^2\eta)_{\text{crit}} = 1.314$. Both points B_1 and B_2 tend towards zero with increasing q^α . All lines separating the different phases correspond to second-order phase transitions.	119
3.5	Expected phase diagram for the 3-dimensional non-compact Higgs model at zero temperature for any q^α . Axis $ \psi ^2 = 0$ corresponds to the (non-compact) pure $U(1)$ gauge model, axis $e^2 = 0$ to the XY model and axis $ \psi ^2 = \infty$ is the Peskin model. Point A is the critical value of the 3-dimensional XY model: $(a \psi ^2/\eta)_{\text{crit}} = 0.322$; point B denotes the critical value of the 3-dimensional Peskin model: $(aq^2e^2\eta)_{\text{crit}} = 12.71$. The short solid-dashed part of line AB near to A denotes first-order transitions; the rest of AB is expected to be of second-order kind. Point tc denotes the tricritical point separating the segment of first-order transitions from the line of transitions of second-order type.	121
3.6	Expected phase diagram for the 2-dimensional compact and non-compact Higgs model: left, for $q^\alpha = 1$, and right, for $q^\alpha \neq 1$. Point A denotes the Kosterlitz-Thouless transition of the 2-dimensional XY model, $(\psi ^2/\eta)_{\text{crit}} = 0.637$, which remains isolated. The area-decay of the only phase displayed has nothing to do with sessile dislocations but with the very dimensionality of the lattice.	124

- 3.7 Left and middle, expected phase diagram for the 4-dimensional compact Higgs model with $q^\alpha = 2$ and q^α large, respectively; right, phase diagram for the 4-dimensional non-compact Higgs model with $q^\alpha > 1$. Point A is the critical value of the XY model: $(a^2|\psi|^2/\eta)_{\text{crit}} = 0.526$. Left point B is the first-order transition point of the pure $Z(2)$ gauge model: $(e^2\eta)_{\text{crit}} = 2.268$; right point B is the critical value of the Peskin model: $(q^2e^2\eta)_{\text{crit}} = 25.11$; point E denotes the second-order transition point of the pure compact $U(1)$ gauge model: $(e^2\eta)_{\text{crit}} = 1.572$. In the middle diagram, B_1 decreases like $1/q^2$ and B_2 tends to the critical value of the pure compact $U(1)$ model when $q^\alpha \rightarrow \infty$. Solid-dashed lines are lines of first-order phase-transitions and solid lines of second-order type. Point D or tc denotes a tricritical point separating the segment of first-order transitions from the line of second-order transitions. 133
- 3.8 Expected phase diagram for the 3-dimensional compact Higgs model with $q^\alpha = 2$ showing the dependence on the temperature through the periodic lattice's length from $\omega = \infty$ (no periodicity, $T = 0$) to a very small ω (high T). Point A' is given by $\frac{a|\psi|^2}{\eta} = \frac{2 ak_B T}{\pi \eta \lambda_{\text{scale}}}$, point B' by $ae^2\eta = 2.268 \frac{ak_B T}{\eta \lambda_{\text{scale}}}$ and point E' by $ae^2\eta = \frac{\pi ak_B T}{2 \eta \lambda_{\text{scale}}}$. Points A and B at $T = 0$ are equal to those in Fig. 3.4, page 119. $\frac{a|\psi|^2}{\eta} = 0.322$ and $ae^2\eta = 1.314$ respectively. All lines are lines of second-order phase transitions. 136
- 3.9 Expected phase diagram for the 3-dimensional compact Higgs model with large q^α showing the dependence on the temperature through the periodic lattice's length from $\omega = \infty$ (no periodicity, $T = 0$) to a very small ω (high T). Point A' is given by $\frac{a|\psi|^2}{\eta} = \frac{2 ak_B T}{\pi \eta \lambda_{\text{scale}}}$ and point E' by $ae^2\eta = \frac{\pi ak_B T}{2 \eta \lambda_{\text{scale}}}$. Point B'_2 tends toward the value of E' in the limit $q^\alpha \rightarrow \infty$. Both point B'_1 and point B_1 decreases with increasing q^α like $1/q^2$; transition point B_2 tends to $e^2 = 0$ too, since the 3-dimensional $U(1)$ gauge model displays no phase transition points at $T = 0$. Point A is equal to $\frac{a|\psi|^2}{\eta} = 0.322$. Both solid lines at $T = 0$ are expected to be formed by second-order transition points, whilst the dashed-solid lines (high T) are formed by transition points of Kosterlitz-Thouless type. 137

- 3.10 Expected phase diagram for the 3-dimensional non-compact Higgs model with any q^α showing the dependence on the temperature through the periodic lattice's length from $\omega = \infty$ (no periodicity, $T = 0$) to a very small ω (high T). Point A' is given by $\frac{a|\psi|^2}{\eta} = \frac{2 ak_B T}{\pi \eta \lambda_{\text{scale}}}$ and point B' by $ae^2\eta = \frac{8\pi ak_B T}{q^2 \eta \lambda_{\text{scale}}}$. Points A and B at $T = 0$ are equal to those in Fig. 3.5 on page 121: $\frac{a|\psi|^2}{\eta} = 0.322$ and $ae^2\eta = \frac{12.71}{q^2}$ respectively. Dashed-solid line $P'B'$ at small ω is formed by Kosterlitz-Thouless transition points; short segment $A'P'$ is expected to be of first-order type. At $T = 0$, except for the short segment represented by a dashed-dashed line which starts at A and finishes at the tricritical point tc , segment where the phase transitions are of first-order kind, the rest of line AB is of second-order type. 138
- 3.11 Expected phases of the effective potential in first approximation for the 3-dim. Abrikosov model. Stage I ① gets characterized by symmetry breaking, by a nonvanishing expectation value of the effective potential's scalar field. Well developed Stage III ④ denotes the state of unimpeded spreading out of the density of gliding dislocations, with its associated loss of rigidity, and corresponds to a zero expectation value $\bar{\rho}^2 = 0$ as lowest minimum of the effective potential. Value k_1 is defined by $k = \frac{1}{4\pi\sqrt{|\alpha|_{\text{ren}}}} \sqrt{\frac{(\eta e^2)^3}{\eta|\beta|_{\text{ren}}}} = \frac{3}{2}$ 139
- B.1 Different forms to wrap a rubber band around a ring. 191
- B.2 All loops on a spherical surface can be shrunk to a point. 192
- B.3 Screw dislocation represented by means of complex scalar field ψ , whose orientation in an internal plane indicates the displacement in the physical space of each lattice cell. Covering circumference $C = S^1$, around and arbitrarily distant from the dislocation, ψ draws a complete internal rotation. 198
- B.4 Twist produced by a rotation through angle $\chi = 2\pi$, $\chi = 4\pi$ and $\chi = -2\pi$ of a pencil hung and anchored by two rubber bands. 227
- B.5 Unravelling the $\chi = 4\pi$ twist by deforming the rubber bands. 228
- B.6 Topologically stable loop on a sphere with the opposite points identified ($\tilde{A} \equiv A$). 228
- B.7 The resulting loop of the reaction between two $SO(3)$ stable loops can be deformed to a point. 229
- B.8 One topologically stable map (or loop) from the contour S_∞^1 in physical space defined by azimuthal angle $0 \leq \phi \leq 2\pi$ onto isodirection Θ of the two isovectors entering in isotensor Ψ^{ab} for $H = N(SO(2))$: $\tilde{\Psi}^a(\phi) = \text{length} \times (\sin(\phi/2), 0, \cos(\phi/2))$ 282

B.9	One topologically stable map (or loop) from the distant contour S_∞^1 in physical space defined by azimuthal angle $0 \leq \phi \leq 2\pi$ onto the directions of the two isovectors which are combined into Ψ^{ab} , isovectors which for $H = D_2$ form always an angle $\Theta_0 \neq 0$. Iovector $\tilde{\Psi}^a$ is given, up to its length, by an equation similar to that of Ψ^a but with the change $\Theta_0/2 \rightarrow -\Theta_0/2$	286
C.1	In a 2-dimensional Ising model, a large contour which surrounds only one of the ending points $\vec{r}_{1,2}$ can be placed at $ \vec{r}_2 - \vec{r}_1 \omega(\beta)/4$ positions.	324
C.2	Dislocation pair and its representation by means of "arrow" $S_{\vec{r}}^{\text{scalar}}$, with scalar field $\psi_{\vec{r}} = \psi S_{\vec{r}}^{\text{scalar}}$	348
C.3	Large dislocation pair formed by nearly isolated dislocations.	358
C.4	In a 2-dimensional lattice, a long line of flipped arrows costs energetically only the first and the last frustated plaquette.	415
C.5	$a \psi ^2/\eta - ae^2\eta$ diagram for $q = 2$ and a 3-dimensional system. Axis $ \psi ^2 = 0$ corresponds to the (compact) pure $U(1)$ gauge model, axis $e^2 = 0$ to the XY model and axis $ \psi ^2 = \infty$ is the pure $Z(2)$ gauge model. If $q = p = 1$, the value of the correlation function in the $Z(2)$ gauge model is exactly 1. The diagonal line from the lower left corner to the upper right corner corresponds to $m^2 = a^2q^2e^2 \psi ^2 = 1$. Point A is the critical value (or second-order transition point) of the 3-dimensional XY model: $(a \psi ^2/\eta)_{\text{crit}} = 0.322$; point B denotes the critical value of the 3-dimensional $Z(2)$ gauge model: $(ae^2\eta)_{\text{crit}} = 1.314$	448
C.6	Expected phase diagram for the 3-dimensional compact Higgs model with $q = 2$. Solid line AB is a line of second-order phase transitions.	449
C.7	Expected phase diagram for the 3-dimensional compact Higgs model with $q = p = 1$. Inside the shaded region, no transition occurs, unlike the $q \neq p = 1$ case.	450
C.8	Expected phase diagram for the 3-dimensional non-compact Higgs model for any q . Point A is the critical value of the 3-dimensional XY model: $(a \psi ^2/\eta)_{\text{crit}} = 0.322$; point B denotes the critical value of the 3-dimensional Peskin model: $(aq^2e^2\eta)_{\text{crit}} = 12.71$. The short solid-dashed part of line AB near to A denotes first order-transitions; the rest of AB is expected to be of second-order kind. Point tc denotes the tricritical point separating the segment of first-order transitions from the line of transitions of second-order type.	465
C.9	Expected phase diagram for the 4-dimensional non-compact Higgs model for $q > 1$. Point A is the critical value of the 4-dimensional XY model: $(a^2 \psi ^2/\eta)_{\text{crit}} = 0.526$; point B denotes the critical value of the 4-dimensional Peskin model: $(q^2e^2\eta)_{\text{crit}} = 25.11$. The short solid-dashed part of line AB near to A denotes first order-transitions; the rest of AB is expected to be of second-order type. Point tc denotes the tricritical point separating the segment of first-order transitions from the line of transitions of second-order type. For $q = 1$ there is the minor change of $W(C) = 1$ at small e^2 and $ \psi ^2 = \infty$	477

- C.10 Expected phase diagram for the 4-dimensional compact Higgs model for large q (left) and $q = 2$ (right). Point A is the critical value of the 4-dimensional XY model: $(a^2|\psi|^2/\eta)_{\text{crit}} = 0.526$; point B denotes the first-order transition point of the pure $Z(2)$ gauge model: $(e^2\eta)_{\text{crit}} = 2.268$; point E represents the second-order transition point of the pure compact $U(1)$ gauge model: $(e^2\eta)_{\text{crit}} = 1.572$. Point B_1 decreases like $1/q^2$ and point B_2 tends to the critical value of the pure compact $U(1)$ model when $q \rightarrow \infty$. Solid-dashed lines are lines of first-order phase-transitions and solid lines of second-order type. Point tc or D denotes the tricritical point separating the segment of first-order transitions from the line of transitions of second-order type. 481
- C.11 Expected phase diagram for the 2-dimensional compact and non-compact Higgs model: left, for $q = 2 \neq p = 1$, and right, for $q = 1$. Point A denotes the Kosterlitz-Thouless transition of the 2-dimensional XY model: $(|\psi|^2/\eta)_{\text{crit}} = 0.637$ 487
- D.1 Trajectories followed by the parameters of the 2-dim. XY model during the process of coarse graining (or defocussing). 570
- D.2 Expected phase diagram for the 3-dimensional compact Higgs model with $q = 2$ showing the dependence on the periodic lattice's length from $\omega = \infty$ (no periodicity) to a very small ω . Point A' is given by $\frac{a|\psi|^2}{\eta} = \frac{2a}{\pi\omega}$, point B' by $ae^2\eta = 2.268\frac{a}{\omega}$ and point E' by $ae^2\eta = \frac{\pi a}{2\omega}$. Points A and B at $\omega = \infty$ are equal to those in Fig. C.5, page 448: $\frac{a|\psi|^2}{\eta} = 0.322$ and $ae^2\eta = 1.314$ respectively. All lines are lines of second-order phase transitions. A small "pocket" of the phase restricted, at small ω , to $|\psi|^2 = 0$ and small e^2 may exist also for small $|\psi|^2 \neq 0$ for a ω large enough. 747
- D.3 Expected phase diagram for the 3-dimensional compact Higgs model at large q showing the dependence on the periodic lattice's length from $\omega = \infty$ (no periodicity) to a very small ω . Point A' is given by $\frac{a|\psi|^2}{\eta} = \frac{2a}{\pi\omega}$ and point E' by $ae^2\eta = \frac{\pi a}{2\omega}$. Point B'_2 tends toward the value of E' in the limit $q \rightarrow \infty$. Both point B'_1 and point B_1 decreases with increasing q like $1/q^2$; transition point B_2 tends to $e^2 = 0$ too, since the 3-dimensional $U(1)$ gauge model displays no phase transition points at $\omega = \infty$. Point A is equal to $\frac{a|\psi|^2}{\eta} = 0.322$. Both solid lines at $\omega = \infty$ are expected to be formed by second-order transition points, whilst the dashed-solid lines (small ω) are formed by transition points of Kosterlitz-Thouless type. 748

D.4 Expected phase diagram for the 4-dimensional compact Higgs model with $q = 2$ showing the dependence on the periodic lattice's length from $\omega = \infty$ (no periodicity) to a very small ω . Point A' is given by $\frac{a^2|\psi|^2}{\eta} \approx 0.526 \frac{a^2}{\omega^2}$, point B'_1 by $e^2\eta = 2.240 \frac{\omega}{a}$, point B'_2 by $e^2\eta = 4.405 \frac{a}{\omega}$, and point E' by $e^2\eta = 3.106 \frac{a}{\omega}$. Points A, B and E at $\omega = \infty$ are equal to those in the right part of Fig. C.10 on page 481: $\frac{a^2|\psi|^2}{\eta} = 0.526$, $e^2\eta = 2.268$ and $e^2\eta = 1.572$ respectively. Solid lines at small ω are lines of second-order phase transitions, and point tc' denotes the tricritical point separating the first-order-transition segment which starts at A' from the rest of the line of second-order transitions. Dashed-solid (and dashed-dashed) line ADB is a line of first-order phase transitions whilst line ED is of second-order type; point D is another tricritical point. For $\omega = \infty$ in the table above, τ and τ^* denote respectively the length of C and C^* along the, in such a case non-periodic, a_τ -coordinate. For ω large enough one can assume the existence of a small "pocket" connecting the phase restricted, at small ω , to $|\psi|^2 = 0$ and small e^2 , with the same phase occurring at $\omega = \infty$ for a wide range of small e^2 and $|\psi|^2$ 749

D.5 Expected phase diagram for the 4-dimensional compact Higgs model at large q showing the dependence on the periodic lattice's length from $\omega = \infty$ (no periodicity) to a very small ω . Point A' is given by $\frac{a^2|\psi|^2}{\eta} = 0.526 \frac{a^2}{\omega^2}$ and point E' by $e^2\eta = 3.106 \frac{a}{\omega}$. Point B'_2 tends toward the value of E' with increasing q , and point B'_1 decreases like $1/q^2$ due to self-dual relation $(e^2\eta)_{B'_1} = \frac{4\pi^2}{q^2} \frac{1}{(e^2\eta)_{B'_2}}$. Points A and E at $\omega = \infty$ are equal to those in the left part of Fig. C.10 on page 481: $\frac{a^2|\psi|^2}{\eta} = 0.526$ and $e^2\eta = 1.572$ respectively; and analogously as for ω small, point B_2 tends to the value of E in limit $q \rightarrow \infty$ and point B_1 is related to B_2 by means of the same self-duality's equation, which causes that B_1 tends to zero with increasing q . Note the small "pocket" of the phase characterized by $W(C), H(\vec{x}_a^*, \vec{x}_b^*) \sim \text{constant}$: this region gradually disappears in the limit $q \rightarrow \infty$. Except for the short segment represented by a dashed-dashed line which starts at A and finishes at the tricritical point tc , where the phase transitions are of first-order kind, all the other lines are formed by second-order critical points. 750

- D.6 Expected phase diagram for the 3-dimensional non-compact Higgs model at any q showing the dependence on the periodic lattice's length from $\omega = \infty$ (no periodicity) to a very small ω . Point A' is given by $\frac{a|\psi|^2}{\eta} = \frac{2}{\pi} \frac{a}{\omega}$ and point B' by $ae^2\eta = \frac{8\pi}{q^2} \frac{a}{\omega}$. Points A and B at $\omega = \infty$ are equal to those in the left part of Fig. C.8 on page 465: $\frac{a|\psi|^2}{\eta} = 0.322$ and $ae^2\eta = \frac{12.71}{q^2}$ respectively. Dashed-solid line $P'B'$ at small ω is formed by Kosterlitz-Thouless transition points; short segment $A'P'$ is expected to be of first-order type. At $\omega = \infty$, except for the short segment represented by a dashed-dashed line which starts at A and finishes at the tricritical point tc , segment where the phase transitions are of first-order kind, the rest of line AB is of second-order type. 751
- D.7 Expected phase diagram for the 4-dimensional non-compact Higgs model at any q showing the dependence on the periodic lattice's length from $\omega = \infty$ (no periodicity) to a very small ω . Point A' is given by $\frac{a^2|\psi|^2}{\eta} = 0.526 \frac{a^2}{\omega^2}$ and point B' by $e^2\eta = \frac{12.71}{q^2} \frac{\omega}{a}$. Points A and B at $\omega = \infty$ are equal to those in the left part of Fig. C.9 on page 477: $\frac{a^2|\psi|^2}{\eta} = 0.526$ and $e^2\eta = \frac{25.11}{q^2}$ respectively. Except for the short segments represented by the solid-dashed line (at small ω) or by a dashed-dashed line (at $\omega = \infty$) which start at A' or A and finish at a tricritical point tc , segments where the phase transitions are of first-order kind, all the other lines are expected to be formed by second-order critical points. Tricritical point tc tends towards A' with decreasing ω 752
- D.8 Expected phases of the effective potential up to order η for the d -dim. Abrikosov model with $d = 3, 4$. Superconducting phase ① gets characterized by symmetry breaking, by a nonvanishing expectation value of the effective potential's scalar field; phase ④ denotes the normal conducting (or Coulomb) state and corresponds to a zero expectation value $\bar{\rho}^2 = 0$ as lowest minimum of the effective potential. Value k_1 is defined by $k = \frac{11(d-1)}{96\pi^2} \frac{(\eta e^2)^2}{\eta|\beta|_{\text{ren}}} = \frac{22}{19}$ for $d = 4$ and by $k = \frac{(d-1)}{8\pi\sqrt{|\alpha|_{\text{ren}}}} \sqrt{\frac{(\eta e^2)^3}{\eta|\beta|_{\text{ren}}}} = \frac{3}{2}$ for $d = 3$ 753

List of Tables

2.1	Definitions of the gliding and primary dislocation density and current with only one slip system activated.	37
2.2	Analogy between the equations of the Maxwell theory and those of dislocation dynamics for single slip, in the primary slip system. Fields $\varrho_{m\mathbf{g}}^\alpha$ and $\mathbf{j}_{m\mathbf{g}}^\alpha$ takes account of the sessile dislocations, whose Burgers is not completely contained in the primary plane. But in the case of only one active slip system, sessile dislocations are not produced and thus $\varrho_{m\mathbf{g}}^\alpha \approx \mathbf{j}_{m\mathbf{g}}^\alpha \approx 0$	47
2.3	Definitions and equations for the density and current for dislocations whose Burgers vector is completely parallel to some of the slip planes, distinguishing the contribution due to the actual gliding dislocations from that arising from pinned dislocations but which otherwise would be able to glide.	52
2.4	Analogies between the states displayed by the Abrikosov model of superconductivity and the stages shown by a crystal containing dislocations.	54
2.5	Correspondence among the parameters of the Abrikosov model and those of the dislocation model.	88
2.6	Behaviour of the correlation functions for the 3-dimensional lattice dislocation model (analogue to the 3-dim. lattice Higgs model) at very low temperatures, showing the correspondence to the different hardening stages.	106
C.1	Ising spin correlation for a 2-dimensional lattice.	329
C.2	Correlation in the 2-dimensional XY model.	359
C.3	Correlation in 3-dimensional XY model.	382